Application Serial No. 10/068,184 Amendment mailed January 28, 2004 Reply to Office Action of April 28, 2004

LISTING OF CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

- 1. (currently amended) A coiled air brake tubing comprising a laminated tube said tube having an innermost layer of nylon, an intermediate layer of a polyurethane and an outermost layer of nylon wherein said tubing is set in a coiled configuration, and said outermost layer is in direct contact with an entire surface of a next adjacent inner layer.
- 2. (currently amended) The method coiled tubing claimed in claim 1 wherein said polyurethane is selected from the group consisting of polyether polyurethane and polyester polyurethane.
- 3. (original) The coiled tubing claimed in claim 1 further comprising a fiber reinforcing layer within said polyurethane layer.
- 4. (original) The coiled tubing claimed in claim 3 wherein said fiber layer is a polyester layer.
- 5. (original) The coiled tubing claimed in claim 3 wherein said fiber reinforcing layer includes three to six pics per inch.

Application Serial No. 10/068,184 Amendment mailed January 28, 2004 Reply to Office Action of April 28, 2004

- 6. (original) The coiled tubing claimed in claim 1 wherein said innermost layer of nylon is from about 2 to about 5 mills.
- 7. (currently amended) The method coiled tubing claimed in claim 1 wherein said nylon layers are selected from the group consisting of nylon 6, nylon 11 and nylon 12 and alloys thereof.
- 8. (currently amended) The method coiled tubing claimed in claim 1 wherein said polyurethane layer is a polyether polyurethane.
- 9. (original) The coiled tubing claimed in claim 8 wherein said polyurethane has a hardness of 80A-63D.
- 10. (withdrawn) The method of forming a coiled laminated air brake tubing comprising co-extruding an innermost nylon layer and a first polyurethane layer;

forming a fiber reinforcing layer over said first polyurethane layer; applying a solvent to said first polyurethane layer;

extruding a second polyurethane layer over said fiber reinforcing layer and said first polyurethane layer; and

extruding an outermost nylon layer over said second polyurethane layer.

Application Serial No. 10/068,184 Amendment mailed January 28, 2004 Reply to Office Action of April 28, 2004

11. (withdrawn) The method claimed in claim 10 wherein said solvent is selected from the group consisting of N-methyl pyrrolidone and diemethyl formamide.